

Nominal Dimensions	1" (25.4mm) Wide x 18" (45.7 cm) Long x 0.004" Thick
ASTM F152 - Copper Strip	C11000 Electrolytic Tough Pitch
Chemical Properties	Minimum 99.90% Copper
Electrical Conductivity	100.000 % IACS @ 68° F (annealed) 58.108 MS/m @ 68° F (annealed)
Electrical Resistance	0.0172 Ω / M
Density	0.322 pounds / cubic inch @ 68° F (annealed)
Modulus	17000 Elastic Modulus in tension ksi
Acclimation Time	48 Hours
Service & Storage Temperature	65° - 85° F <i>See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures.</i>
Warranty	Lifetime Electrical Resistance
Approved Adhesives	Excelsior ASD-800, Wet-Set Acrylic ESD Adhesive Excelsior USD-810, Urethane Two-Part ESD Adhesive
Technical Support	solutions@rhctechical.com
Product Support	info@flexcofloors.com
Technical Documentation	www.flexcofloors.com