

Rubber Stair Tread Product Submittal

1975 HEAVY DUTY HAMMERED ONE PIECE STAIR TREAD / RISER with INSERTS

Available Lengths	36", 42", 48", 54", 60", 66", 72", 78", 84", 90", 96", 102", & 108"	
Finish	SE Hammered Design	
Nose Configuration	Square Nose	
Available Abrasive Strip Colors	White, Gray, Brown, Black, Canary, & Glow Strip	
Available Ribbed/Smooth Rubber Inserts	All 57 FlexTones® Colors, plus Canary Yellow	
ASTM F2169 - Resilient Stair Treads	Type TS, Class 2, Group 1 & 2, Grade 1	
ASTM E648 (NFPA 253) - Critical Radiant Flux	Class 1, ≥ 0.45 W/cm ²	
ASTM E662 (NFPA 258) - Smoke Density	Passes, ≤ 450	
CAN/ULC-S102.2 - Surface Burning	115 Flame Spread Rating 275 Smoke Developed Classification	
ASTM D2047 - Static Coefficient of Friction	≥ 0.50	

ADA Standards for Accessible Design states the floor surface shall be stable, firm and slip resistant. Our test results utilize the James Machine as described in D2047 and as described in UL410 for floor covering materials (FCM) utilizing a leather foot under dry conditions. Maintenance processes and commonly utilized site applied finishes, polishes and other sealers to maintain resilient flooring products will change the walking surface and ultimately the Static Coefficient of Friction.

ASTM F925 - Chemical Resistance

Excellent with chemicals listed in standard, Additional chemicals available via chart

ASTM F925 testing is utilized to ensure flooring materials will stand up to certain household standard chemistries. Additional chemical resistance testing performed using this test method is for informational and guidance purposes only. Proper maintenance will have an effect on chemical resistance, but the best defense against a negative effect is to clean the drop/spill from the flooring surface immediately.

ASTM F1514 - Heat Stability	Excellent, $\Delta E \le 8$
Sustainability Information	Made in the U.S.A.
	Meets Buy America Act (49 CFR Part 661)
	Meets Buy American Act (41 USC §§ 8301-8303)
	Contributes to LEED v4/4.1
	FloorScore Certification
	Meets CA 01350 Requirements
	Meets CHPS Requirements
	NSF/ANSI 332 Platinum Certification
	HPD Available
	Contains No Recycled Content
	Red List Chemical Free
Acclimation Time	48 Hours
Service & Storage Temperature	65° - 85° F
See installation document for full installation deta	ails regarding approved substrates, job site conditions and acclimation procedures.

Product Warranty

10 Years

See product warranty for full details regarding limitations and warranty coverage.



Rubber Stair Tread Product Submittal

1975 HEAVY DUTY HAMMERED ONE PIECE STAIR TREAD / RISER with INSERTS

Approved Adhesives	Excelsior EN-610, Epoxy Nose Filler	
	Excelsior TP-620, Pressure Sensitive Tread Tape	
	Excelsior AW-510, Wet-Set Acrylic	
	Excelsior C-631, Contact Adhesive	
	Excelsior U-705, Urethane Wet-Set	
	Excelsior EW-710, Urethane Enhanced Epoxy Adhesive	
Technical Support	solutions@rhctechnical.com	
Product Support	info@flexcofloors.com	
Technical Documentation	www.flexcofloors.com	

13/64* 11/16*		- 5/64
⊢ <u>⊤</u> 1-5/8* ⊥	20-3/8"	= 5/64

Attach Color Sample Here

Butting Treads & Pattern Alignment

Wider stairwells and stairwells that require pattern alignment will require additional planning and dry fitting prior to installation. We recommend ordering treads the next size up to achieve these layouts and installations. Our treads are manufactured to be trimmed on each end of the length and the depth of the tread.

EN-610 Epoxy Nose Filler

The predominant step being used in construction today is the metal formed frame with a pan filled with concrete, having a nose radius of 1/2" maximum as spelled out in the ADA guidelines. When installing Rubber Stair Treads on these substrates, either new construction or remodel, they do not require the use of the EN-610 Epoxy Nose Filler. Fitting the tread properly to the step and creating a tight fit to the substrate will ensure proper installation and performance of the Stair Tread.

For installations that occur on other substrates (worn metal, wood, existing approved flooring types), the EN-610 Nose Filler may be required to ensure proper fit to the substrate. These substrates need to be verified for uneven wear and corrected appropriately using the best means available. One of these means is the EN-610 Epoxy Nose Filler. It is our recommendation to check for gaps between the radius in the nose of the tread and the substrate. If a gap greater than 1/4" is present, it is required to use the EN-610 Epoxy Nose Filler. If a gap of 1/2" or greater is present, the substrate should be prepared using other methods.

Of course, with any Stair Tread installation it is acceptable to utilize the EN-610 Epoxy Nose Filler.