

Vinyl Stair Tread Product Submittal

VT ROUND NOSE

Finish Ribbed Nose Configuration Round Bull Nose ASTM F2169 - Resilient Stair Treads Type TP, Class 2, Group 1 & 2, Grade 1 ASTM E648 (NFPA 253) - Critical Radiant Flux Class 1, ≥ 0.45 W/cm² ASTM E662 (NFPA 258) - Smoke Density Passes, ≤ 450 ASTM D2047 - Static Coefficient of Friction ADA Standards for Accessible Design states the floor surface shall be stable, firm and slip resistant. Our test results utilize the James Machine as described in D2047 and as described in UL410 for floor covering materials (FCM) utilizing a leather foot under dry conditions. Maintenance processes and commonly utilized site applied finishes, polishes and other sealers to maintain resilient flooring products will change the walking surface and utilimately the State Coefficient of Friction ASTM F925 - Chemical Resistance Excellent with chemicals listed in standard, Additional chemicals available via chart ASTM F925 testing is utilized to ensure flooring materials will stand up to certain household standard chemistries. Additional chemical resistance testing performed using this test method is for informational and guidance purposes only. Proper maintenance will have an effect on chemical resistance, but the best defense against a negative effect is to clean the drop/spill from the flooring surface immediately. ASTM F1514 - Heat Stability Excellent, ∆E ≤ 8 Sustainability Information Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements Acclimation Time 48 Hours Service & Storage Temperature 66° - 85° F See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty 5 Years See product warranty for full details regarding ilmitations and warranty coverage.	Naminal Dimensions	26" 42" 40" 9 72"
Nose Configuration Round Bull Nose ASTM F2169 - Resilient Stair Treads Type TP, Class 2, Group 1 & 2, Grade 1 ASTM E648 (NFPA 253) - Critical Radiant Flux Class 1, ≥ 0.45 W/cm² ASTM E662 (NFPA 258) - Smoke Density Passes, ≤ 450 ASTM D2047 - Static Coefficient of Friction ≥ 0.50 ADA Standards for Accessible Design states the floor surface shall be stable. Ifm and silp resistant. Our test results utilize the James Machine as described in 2014 and as described in 2014 for floor covering materials (FCM) utilizing a leather foot under dry conditions. Maintenance processes and commonly utilized site applied finishes, polishes and other sealers to maintain resilient flooring products will change the walking surface and utilimately the Static Coefficient of Friction. ASTM F925 - Chemical Resistance Excellent with chemicals listed in standard, Additional chemicals available via chart ASTM F925 testing is utilized to ensure flooring materials will stand up to certain household standard chemistries. Additional chemical resistance testing performed using this test method is for informational and guidance purposes only. Proper maintenance will have an effect on chemical resistance, but the best defense against a negative effect is to clean the drop/spill from the flooring surface immediately. ASTM F1514 - Heat Stability Excellent, ΔΕ ≤ 8 Sustainability Information Made in the U.S.A. Meets Buy America Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorSco	Nominal Dimensions	
ASTM F2169 - Resilient Stair Treads Type TP, Class 2, Group 1 & 2, Grade 1 ASTM E648 (NFPA 253) - Critical Radiant Flux Class 1, ≥ 0.45 W/cm² ASTM E662 (NFPA 258) - Smoke Density Passes, ≤ 450 ASTM D2047 - Static Coefficient of Friction ADA Standards for Accessible Design states the floor surface shall be stable, firm and slip resistant. Our test results utilize the James Machine as described in D247 and as described in D247 of floor covering materials (FCM) utilizing a leather foot under dry conditions. Maintenance processes and commonly utilized site applied finishes, polishes and other sealers to maintain resilient flooring products will change the walking surface and ultimately the Static Coefficient of Friction. ASTM F925 - Chemical Resistance Excellent with chemicals listed in standard, Additional chemicals available via chart ASTM F925 testing is utilized to ensure flooring materials will stand up to certain household standard chemistries. Additional chemical resistance between the stating performed using this test method is for informational and guidance purposes only. Proper maintenance will have an effect on chemical resistance, but the best defense against a negative effect is to clean the drop/spill from the flooring surface immediately. ASTM F1514 - Heat Stability Excellent, ∆E ≤ 8 ASTM F1515 - Light Stability Excellent, ∆E ≤ 8 Sustainability Information Made in the U.S.A. Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements Acclimation Time 48 Hours Service & Storage Temperature 5° - 8° F See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior AW-510, Wet-Set Acrylic		
ASTM E648 (NFPA 253) - Critical Radiant Flux ASTM E662 (NFPA 258) - Smoke Density Passes, ≤ 450 ASTM D2047 - Static Coefficient of Friction ADA Standard for Accessible Design states the floor surface shall be stable, firm and slip resistant. Our test results utilize the James Machine as described in D2047 and as described in UL+10 for floor covering materials (FCM) utilizing a leather foot under dry conditions. Maintenance processes and commonly utilized site applied finishes, polishes and other sealers to maintain resilient flooring products will change the walking surface and ultimately the Static Coefficient of Friction ASTM F925 - Chemical Resistance Excellent with chemicals listed in standard, Additional chemicals available via chart ASTM F925 testing is utilized to ensure flooring materials will stand up to certain household standard chemistries. Additional chemical resistance testing performed using this test method is for informational and guidance purposes only. Proper maintenance will have an effect on chemical resistance, but the best defense against a negative effect is to clean the drop/spill from the flooring surface immediately. ASTM F1514 - Heat Stability Excellent, △E ≤ 8 ASTM F1515 - Light Stability Excellent, △E ≤ 8 Sustainability Information Made in the U.S.A. Meets Buy American Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements Acclimation Time 48 Hours Service & Storage Temperature 66° - 85° F See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty 5 Years See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AV-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive	Nose Configuration	Round Bull Nose
ASTM E662 (NFPA 258) - Smoke Density ASTM D2047 - Static Coefficient of Friction ≥ 0.50 ADA Standards for Accessible Design states the floor surface shall be stable, firm and slip resistant. Our test results utilize the James Machine as described in D2047 and as described in D2047 and so described	ASTM F2169 - Resilient Stair Treads	Type TP, Class 2, Group 1 & 2, Grade 1
ASTM D2047 - Static Coefficient of Friction ≥ 0.50 ADA Standards for Accessible Design states the floor surface shall be stable, firm and slip resistant. Our test results utilize the James Machine as described in UL410 for floor covering materials (FCM) utilizing a leather foot under dry conditions. Maintenance processes and commonly utilized site applied finishes, polishes and other sealers to maintain resilient flooring products will change the walking surface and utilimately the Static Coefficient of Friction. ASTM F925 - Chemical Resistance Excellent with chemicals listed in standard, Additional chemicals available via chart ASTM F925 testing is utilized to ensure flooring materials will stand up to certain household standard chemistries. Additional chemical resistance testing performed using this test method is for informational and guidance purposes only. Proper maintenance will have an effect on chemical resistance, but the best defense against a negative effect is to clean the drop/spill from the flooring surface immediately. ASTM F1514 - Heat Stability Excellent, ΔΕ ≤ 8 ASTM F1515 - Light Stability Excellent, ΔΕ ≤ 8 Sustainability Information Made in the U.S.A. Meets Buy American Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements Acclimation Time 48 Hours Service & Storage Temperature 65° - 85° F See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty 5 Years See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive	ASTM E648 (NFPA 253) - Critical Radiant Flux	Class 1, ≥ 0.45 W/cm ²
ADA Standards for Accessible Design states the floor surface shall be stable, firm and slip resistant. Our test results utilize the James Machine as described in D2047 and as described in UL410 for floor covering materials (FCM) utilizing a leather foot under dry conditions. Maintenance processes and commonly utilized site applied finishes, polishes and other sealers to maintain resilient flooring products will change the walking surface and utilimately the Static Coefficient of Friction. ASTM F925 - Chemical Resistance Excellent with chemicals listed in standard, Additional chemical resistance testing performed using this test method is for informational and guidance purposes only. Proper maintenance will have an effect on chemical resistance, but the best defense against a negative effect is to clean the drop/spill from the flooring surface immediately. ASTM F1514 - Heat Stability Excellent, ∆E ≤ 8 ASTM F1515 - Light Stability Excellent, ∆E ≤ 8 Sustainability Information Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy America Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements Acclimation Time 48 Hours Service & Storage Temperature 65° - 85° F See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty 5 Years See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior EN-610, Pressure Sensitive Tread Tape Excelsior C-631, Contact Adhesive	ASTM E662 (NFPA 258) - Smoke Density	Passes, ≤ 450
described in D2047 and as described in UL410 for floor covering materials (FCM) utilizing a leather foot under dry conditions. Maintenance processes and commonly utilized site applied finishes, polishes and other sealers to maintain resilient flooring products will change the walking surface and utilimately the Static Coefficient of Friction. ASTM F925 - Chemical Resistance Excellent with chemicals listed in standard, Additional chemicals available via chart ASTM F925 testing is utilized to ensure flooring materials will stand up to certain household standard chemicals resistance testing performed using this test method is for informational and guidance purposes only. Proper maintenance will have an effect on chemical resistance, but the best defense against a negative effect is to clean the drop/spill from the flooring surface immediately. ASTM F1514 - Heat Stability Excellent, △E ≤ 8 Sustainability Information Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements Acclimation Time 48 Hours Service & Storage Temperature 65° - 85° F See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty 5 Years See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior C-631, Contact Adhesive	ASTM D2047 - Static Coefficient of Friction	≥ 0.50
ASTM F925 - Chemical Resistance ASTM F925 testing is utilized to ensure flooring materials will stand up to certain household standard chemistries. Additional chemical resistance testing performed using this test method is for informational and guidance purposes only. Proper maintenance will have an effect on chemical resistance, but the best defense against a negative effect is to clean the drop/spill from the flooring surface immediately. ASTM F1514 - Heat Stability Excellent, ∆E ≤ 8 ASTM F1515 - Light Stability Excellent, ∆E ≤ 8 Sustainability Information Made in the U.S.A. Meets Buy American Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements Acclimation Time 48 Hours Service & Storage Temperature 65° - 85° F See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty 5 Years See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive	described in D2047 and as described in UL410 for floor covering material and commonly utilized site applied finishes, polishes and other sea	erials (FCM) utilizing a leather foot under dry conditions. Maintenance processes alers to maintain resilient flooring products will change the walking surface and
testing performed using this test method is for informational and guidance purposes only. Proper maintenance will have an effect on chemical resistance, but the best defense against a negative effect is to clean the drop/spill from the flooring surface immediately. ASTM F1514 - Heat Stability Excellent, △E ≤ 8 ASTM F1515 - Light Stability Excellent, △E ≤ 8 Sustainability Information Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements Acclimation Time 48 Hours Service & Storage Temperature 5° - 85° F See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty 5 Years See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive	ASTM F925 - Chemical Resistance	
ASTM F1515 - Light Stability Sustainability Information Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements Acclimation Time 48 Hours Service & Storage Temperature See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty 5 Years See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive	testing performed using this test method is for informational and g	guidance purposes only. Proper maintenance will have an effect on chemical
Sustainability Information Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements Acclimation Time 48 Hours Service & Storage Temperature 65° - 85° F See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty 5 Years See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive	ASTM F1514 - Heat Stability	Excellent, ∆E ≤ 8
Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements Acclimation Time 48 Hours Service & Storage Temperature 65° - 85° F See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty 5 Years See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive	ASTM F1515 - Light Stability	Excellent. ∧E ≤ 8
Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements Acclimation Time 48 Hours Service & Storage Temperature 65° - 85° F See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty 5 Years See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive	3 3 3 3 3 3 3 3 3 3 3 3 3 3 3 3 3 3 3 3	
Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements Acclimation Time 48 Hours Service & Storage Temperature 65° - 85° F See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty 5 Years See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive		
Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements Acclimation Time 48 Hours Service & Storage Temperature 65° - 85° F See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty 5 Years See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive		Made in the U.S.A.
Acclimation Time 48 Hours Service & Storage Temperature 5° - 85° F See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty 5 Years See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive		Made in the U.S.A. Meets Buy America Act (49 CFR Part 661)
Acclimation Time Service & Storage Temperature See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty 5 Years See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive		Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303)
Service & Storage Temperature See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive	Sustainability Information	Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1
Service & Storage Temperature See installation document for full installation details regarding approved substrates, job site conditions and acclimation procedures. Product Warranty See product warranty for full details regarding limitations and warranty coverage. Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive		Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification
Product Warranty 5 Years See product warranty for full details regarding limitations and warranty coverage. Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive		Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements
Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive	Sustainability Information Acclimation Time	Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements 48 Hours
Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive	Sustainability Information Acclimation Time Service & Storage Temperature	Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements 48 Hours 65° - 85° F
Approved Adhesives Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive	Sustainability Information Acclimation Time Service & Storage Temperature See installation document for full installation details regarding	Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements 48 Hours 65° - 85° F ag approved substrates, job site conditions and acclimation procedures.
Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive	Sustainability Information Acclimation Time Service & Storage Temperature See installation document for full installation details regarding. Product Warranty	Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements 48 Hours 65° - 85° F ag approved substrates, job site conditions and acclimation procedures. 5 Years
Excelsior AW-510, Wet-Set Acrylic Excelsior C-631, Contact Adhesive	Acclimation Time Service & Storage Temperature See installation document for full installation details regarding Product Warranty See product warranty for full details	Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements 48 Hours 65° - 85° F In approved substrates, job site conditions and acclimation procedures. 5 Years Is regarding limitations and warranty coverage.
Excelsior C-631, Contact Adhesive	Sustainability Information Acclimation Time Service & Storage Temperature See installation document for full installation details regarding	Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements 48 Hours 65° - 85° F ag approved substrates, job site conditions and acclimation procedures. 5 Years s regarding limitations and warranty coverage. Excelsior EN-610, Epoxy Nose Filler
·	Sustainability Information Acclimation Time Service & Storage Temperature See installation document for full installation details regarding Product Warranty See product warranty for full details	Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements 48 Hours 65° - 85° F In approved substrates, job site conditions and acclimation procedures. 5 Years Is regarding limitations and warranty coverage. Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape
Excelsior U-705, Urethane Wet-Set	Sustainability Information Acclimation Time Service & Storage Temperature See installation document for full installation details regarding Product Warranty See product warranty for full details	Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements 48 Hours 65° - 85° F In approved substrates, job site conditions and acclimation procedures. 5 Years Is regarding limitations and warranty coverage. Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape
	Acclimation Time Service & Storage Temperature See installation document for full installation details regarding Product Warranty See product warranty for full details	Made in the U.S.A. Meets Buy America Act (49 CFR Part 661) Meets Buy American Act (41 USC §§ 8301-8303) Contributes to LEED v4/4.1 FloorScore Certification Meets CA 01350 Requirements 48 Hours 65° - 85° F The approved substrates, job site conditions and acclimation procedures. 5 Years 18 regarding limitations and warranty coverage. Excelsior EN-610, Epoxy Nose Filler Excelsior TP-620, Pressure Sensitive Tread Tape Excelsior AW-510, Wet-Set Acrylic


Excelsior EW-710, Urethane Enhanced Epoxy Adhesive




Vinyl Stair Tread Product Submittal

VT ROUND NOSE

Technical Support	solutions@rhctechnical.com
Product Support	info@flexcofloors.com
Technical Documentation	www.flexcofloors.com





Butting Treads & Pattern Alignment

Wider stairwells and stairwells that require pattern alignment will require additional planning and dry fitting prior to installation. We recommend ordering treads the next size up to achieve these layouts and installations. Our treads are manufactured to be trimmed on each end of the length and the depth of the tread.

EN-610 Epoxy Nose Filler

The predominant step being used in construction today is the metal formed frame with a pan filled with concrete, having a nose radius of 1/2" maximum as spelled out in the ADA guidelines. When installing Rubber Stair Treads on these substrates, either new construction or remodel, they do not require the use of the EN-610 Epoxy Nose Filler. Fitting the tread properly to the step and creating a tight fit to the substrate will ensure proper installation and performance of the Stair Tread.

For installations that occur on other substrates (worn metal, wood, existing approved flooring types), the EN-610 Nose Filler may be required to ensure proper fit to the substrate. These substrates need to be verified for uneven wear and corrected appropriately using the best means available. One of these means is the EN-610 Epoxy Nose Filler. It is our recommendation to check for gaps between the radius in the nose of the tread and the substrate. If a gap greater than 1/4" is present, it is required to use the EN-610 Epoxy Nose Filler. If a gap of 1/2" or greater is present, the substrate should be prepared using other methods.

Of course, with any Stair Tread installation it is acceptable to utilize the EN-610 Epoxy Nose Filler.