

Distinct Designs Rubber Sheet

TECHNICAL DATA

Finish	Smooth
Nominal Dimensions	36" x 20' x 0.100" Rolls
	36" x 20' x 0.100" Rolls
	48" x 20' x 0.100" Rolls
	48" x 40' x 0.100" Rolls
ASTM F1859 - Rubber Sheet without Backing	Type I
ASTM F1859 - Rubber Sheet without Backing	Туре І
ASTM F1859 - Rubber Sheet without Backing ASTM E648 (NFPA 253) - Critical Radiant Flux	Type I Class 1, ≥ 0.45 W/cm ²
ASTM E648 (NFPA 253) - Critical Radiant Flux	
	Class 1, \geq 0.45 W/cm ²
ASTM E648 (NFPA 253) - Critical Radiant Flux ASTM E662 (NFPA 258) - Smoke Density	Class 1, \ge 0.45 W/cm ² Passes, \le 450

ADA Standards for Accessible Design states the floor surface shall be stable, firm and slip resistant. Our test results utilize the James Machine as described in D2047 and as described in UL410 for floor covering materials (FCM) utilizing a leather foot under dry conditions. Maintenance processes and commonly utilized site applied finishes, polishes and other sealers to maintain resilient flooring products will change the walking surface and ultimately the Static Coefficient of Friction.

ASTM F970 - Static Load Resistance

Passes, < 0.005" Indentation @ 250 psi

ASTM F970 - Static Load Resistance, Modified 0.004" Indentation @ 1500 psi

ASTM F970 testing at loads above 250 psi is outside the scope of the test method. Since testing is conducted on flooring product alone, our stated results do not take into consideration chosen adhesive, any utilized underlayments and/or substrates or subfloors. These results should not be construed as an indicator of installed flooring performance.

ASTM F2753 - Rolling Load Limit

≤ 500 lbs / sq. inch

ASTM F2753 testing at loads of 500 lbs force on each wheel after acclimation to laboratory conditions. The Hil-Rom Gurney wheel is utilized for 1,000 cycles and then examinded for indentation, seam condition, tearing or visible issues. Wheels shall not be metal or hard plastic, and the shape of the wheels must be flat with rounded edges, and manufactured with a shore hardness when tested as Type A of \leq 90.

ASTM F925 - Chemical Resistance

Excellent with chemicals listed in standard, Additional chemicals available via chart

ASTM F925 testing is utilized to ensure flooring materials will stand up to certain household standard chemistries. Additional chemical resistance testing performed using this test method is for informational and guidance purposes only. Proper maintenance will have an effect on chemical resistance, but the best defense against a negative effect is to clean the drop/spill from the flooring surface immediately.

ASTM G21 - Resistance to Fungi	Excellent
AATCC 134 - Static Generation	\leq 0.2 kV (200 Volts) with Step, \leq 0.5 kV (500 Volts) with Scuff
ASTM D3389 - Abrasion Resistance	Excellent, ≤ 1 g loss (after 1000 cycles)
ISO 4918 - Castor Chair Test	Excellent, No damage or separation after 25,000 cycles
ASTM F2199 - Dimensional Stability	Excellent, ≤ 0.15%
ASTM F1514 - Heat Stability	Excellent, $\Delta E \leq 8$
ASTM F1515 - Light Stability	Excellent, $\Delta E \le 8$
ASTM C518 - Thermal Resistance, R	Excellent, 0.065 F ft ² h/Btu
ASTM D2240 - Durometer Hardness	Excellent, ≥ 85 Shore A



Distinct Designs Rubber Sheet

TECHNICAL DATA

Acoustical Performance - 6 Inch Concrete Slab

ASTM E2179 - Sound Reduction △IIC 9

Acoustical Performance - 6 Inch Concrete Slab / Ceiling Assembly

ASTM E492 - Impact Insulation Class IIC 51

ASTM E90 - Sound Transmission Class STC 63

The above testing information is provided for informational and guidance when selecting flooring materials. Since testing is conducted on flooring product with or without underlayments and over laboratory substrates these results should not be construed as an indicator or installed flooring performance.

Acclimation Time	48 Hours
Service & Storage Temperature	60° - 85° F
See installation document for full installation details i	regarding approved substrates, job site conditions and acclimation procedures.
Product Warranty	10 Year Commercial Warranty
See product warranty for full details regarding limitat	ions and warranty coverage.
Recommended Adhesives	Excelsior AW-510, Wet-Set Acrylic
	Excelsior PS-525, Modified Pressure Sensitive
	Excelsior U-705, Urethane Wet-Set
	Excelsior EW-710, Urethane Enhanced Epoxy Adhesive
Attributes & Certifications	Made in the U.S.A.
	Meets Buy America Act (49 CFR Part 661, 49 U.S.C. 5323)
	Meets Buy American Act (7 CFR Part 1787, 41 U.S.C 8301-8305)
	Meets Federal Acquisition Regulation (FAR 52.225-9)
	Contributes to LEED v4/4.1
	GREENGUARD Gold Certification
	FloorScore Certification
	Meets CA 01350 Requirements
	Meets CHPS Requirements
	NSF/ANSI 332 Platinum Certification
	EPD Available
	HPD Available
	Contains No Recycled Content
	Red List Chemical Free
Technical Support	solutions@rhctechnical.com
Product Support	info@flexcofloors.com
Technical Documentation	www.flexcofloors.com